

Technical Data Sheet

Rev.1. 21.03.03

APET 026 - APET With Anti UV 100% virgin resin

APET is the favored packaging film worldwide with excellent clarity.
APET is fully recyclable, easily formed & imparts excellent barrier properties in food packaging applications and has a small carbon footprint.

PHYSICAL PROPERTIES

Property	Unit	Nominal Value	Test Method
Specific gravity	g/cm ³	1.34	ASTM D 1503
Tensile strength	kgf/Cm ²	340	ASTM D 882
Izod impact strength @23°C (73°F)	J/m ²	50	ASTM D 256
Heat distortion temp. @0.455mpa (66 psi)	°C	65-70	ASTM D 648
Vicat softening point (@ 5kg load)	°C	71 (+/-2)	ASTM D 1525
Thermoforming Temp.	°C	125-150	-
Light transmission	%	≥90	ASTM D 1003
Surface tension	dyne/Cm	≥38	ASTM D 2578
UV Transmittance (@360nm)	%	0.4	-
Light fastness	ΔE*ab	0.5	ISO4892-2(A)

GENERAL SPECIFICATIONS

- Clear & colors available on request
- Surface silicone & internal antiblock/corona treatment on request
- Antifog & Antistatic coatings on request
- Gauges from 150micron to 1.4mm thickness
- Maximum roll width : 1,800mm
- Standard core diameter 76mm or 152mm

CERTIFICATIONS

- | | |
|---------------------------------------|------------------|
| - USFDA CFR 21 : SECTION 177.1630 | - ISO 9001/14001 |
| - EU 10.2011. Migration | - SGS REACH |
| - CONEG limits on heavy metal content | - SGS EU 94/62 |

All data is based on in-house testing and are believed to be typical values when measured under laboratory condition.
Actual performance of the product described here in, and suitability for use is the responsibility of an end user.